

Amendments to the Claims:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) A coolant ~~for fuel cells that is used to cool down fuel cells~~, comprising:

a water-containing base material; and

a ~~rust~~corrosion-preventive additive that functions to keep an electric conductivity of said coolant ~~for fuel cells~~ at a low level and to maintain a hydrogen ion exponent of said coolant ~~for fuel cells~~ in a substantially neutral level.

2. (Currently Amended) A coolant ~~for fuel cells~~ in accordance with claim 1, wherein the base material is a solution ~~mixture~~-containing a glycol.

3. (Currently Amended) A coolant ~~for fuel cells~~ in accordance with claim 1, wherein the ~~rust~~corrosion-preventive additive includes at least one of an alkalescent-alkaline additive and an ~~acidulous~~-acidic additive.

4. (Currently Amended) A coolant ~~for fuel cells~~ in accordance with claim 1, wherein the ~~rust~~corrosion-preventive additive includes an alkaline additive and an acidic additive.

5. (Currently Amended) A coolant ~~for fuel cells~~ in accordance with claim 4, wherein the alkaline additive is an ethanolamine-series.

6. (Currently Amended) A coolant ~~for fuel cells~~ in accordance with claim 5, wherein the ethanolamine series ~~includes~~ is one of triethanolamine, diethanolamine, and monoethanolamine.

7. (Currently Amended) A coolant ~~for fuel cells~~ in accordance with claim 4, wherein the acidic additive is selected out of the group consisting of triazole compounds, phosphoric acid compounds, and organophosphoric acid compounds.

RECEIVED
MAY 20 2004
TC 1700

8. (Currently Amended) A coolant ~~for fuel cells~~ in accordance with claim 1, wherein the rustcorrosion-preventive additive causes said coolant for fuel cells to have a hydrogen ion exponent of about 6 to 9.

9. (Currently Amended) A coolant ~~for fuel cells~~ in accordance with claim 1, wherein the ~~rust preventive additive causes said coolant for fuel cells to have a low~~ has an electric conductivity of less than about 100 $\mu\text{S}/\text{cm}$.

10. (Currently Amended) A coolant ~~for fuel cells~~ in accordance with claim 1, wherein the rustcorrosion-preventive additive ~~especially has~~ exhibits rustcorrosion-preventive ~~performance~~ characteristics against aluminum material.

11. (Currently Amended) A coolant in accordance with claim 1, wherein the rustcorrosion-preventive additive is a nonionic ~~series~~ substance.

12. (Currently Amended) A coolant in accordance with claim 11, wherein the nonionic ~~series~~ substance includes at least one of a saccharide and a nonionic surfactant.

13. (Previously Presented) A coolant in accordance with claim 11, said coolant is decontaminated by a coolant decontamination system using either one of an ion exchange resin and a chelating resin.

14. (Currently Amended) A coolant in accordance with claim 1, said coolant has undergone ~~deoxidization~~ deoxidation.

N 15. (Withdrawn) A method of enclosing a coolant in accordance with claim 1 in a cooling circuit for a stack of fuel cells, said method comprising the steps of: deoxidizing said coolant; and enclosing said deoxidized coolant with an inert gas in said cooling circuit.

16. (Currently Amended) A cooling ~~system for a stack of fuel cells~~ system, said cooling system comprising: a coolant in accordance with claim 1; and a cooling circuit in which said coolant and an inert gas are enclosed.

17. (Withdrawn) A method of decontaminating a coolant, said method of comprising the steps of:

preparing a water-containing base material;

preparing a rust-preventive additive that functions to keep an electric conductivity of said coolant at a low level and to maintain a hydrogen ion exponent of said coolant in a substantially neutral level; and

removing deteriorating substances from a solution mixture of the base material and the rust-preventive additive with either one of an ion exchange resin and a chelating resin.

18. (New) The coolant according to claim 1, wherein the coolant is used in a fuel cell system.

19. (New) The method of claim 15, wherein the coolant has a conductivity of less than about 100 $\mu\text{S}/\text{cm}$.

20. (New) The method of claim 17, wherein the coolant has a conductivity of less than about 100 $\mu\text{S}/\text{cm}$.